



Torggler Chimica S.p.A.
Via Verande 1/A
39012 – Merano (BZ)
Italy

Eurofins Product Testing A/S
Smedeskovvej 38
DK-8464 Galten
Denmark

Tel. +45 70 22 42 76
Fax +45 70 22 42 75
voc@eurofins.dk
www.eurofins.com/voc-testing

Date
10 January 2020
Our ref.
392-2016-00179804_10

Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

Sample material

| | |
|---|--|
| Sample identification | XTREME GRIP VINYLESTER – Batch No. 1614089 (05-2016) |
| Product type | Multipurpose Construction Adhesive |
| Product data, according to manufacturer | Density: 1.74 g/ml at 20 °C ** Water content: 0 g/l** Exempt compounds: none *** |
| Date received | 09-05-2016 |
| Analytical period | 09-05-2016 – 03-06-2016 |

Methods applied

| Method | Principle | Parameter | Detection limit | Uncertainty, U _m (%) |
|---|-------------|----------------------------------|-----------------|---------------------------------|
| LEED 2009 EQ c4.1 ASTM D 2369 - 10 | Gravimetric | Total Volatiles, SCAQMD rule 304 | 1 g/l | 10 % |
| Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as: ([g all volatiles] - [g water] - [g exempt compounds]) / ([l material] - [l water] - [l exempt compounds]) | | | | |

U_m (%): The expanded uncertainty U_m is equal to 2 x RSD%, see also www.eurofins.dk/uncertainty.

Analytical results

| | Solid content, % mass | Water content, % mass | Exempt compounds, % mass | VOC less water less exempt compounds, g/l | VOC limit g/l |
|-------------------------------|-----------------------|-----------------------|--------------------------|---|---------------|
| XTREME GRIP VINYLESTER | 97.2 | 0** | 0*** | 49 | 70* |

* VOC limit for “Multipurpose Construction Adhesive”

** Given by the client

*** No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Malene Laugesen
Analytical Service Manager

Morten Sielemann
Analytical Chemist