



ETA-Danmark A/S
Göteborg Plads 1
DK-2150 Nordhavn
Tel. +45 72 24 59 00
Internet www.etadanmark.dk

Authorised and notified according
to Article 29 of the Regulation (EU)
No 305/2011 of the European
Parliament and of the Council of 9
March 2011

MEMBER OF EOTA



European Technical Assessment ETA-25/0942 of 2025/10/03

I General Part

Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) No 305/2011: ETA-Danmark A/S

Trade name of the construction product:

Xtreme Epoxy 100

Product family to which the above construction product belongs:

Post-installed rebar connections of the sizes 8 to 40 mm with Torggler Xtreme Epoxy 100 injection mortar

Manufacturer:

Torggler S.r.l.
Via Prati Nuovi 9
IT-39020 Marlengo (BZ)
Tel. +39 0473 282400
Internet www.torggler.com/it/

Manufacturing plant:

Torggler S.r.l.- Manufacturing plant 1

This European Technical Assessment contains:

25 pages including 20 annexes which form an integral part of the document

This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of:

EAD 330087-01-0601, Systems for post-installed rebar connections with mortar

This version replaces:

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (except the confidential Annexes referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

II SPECIFIC PART OF THE EUROPEAN TECHNICAL ASSESSMENT

1 Technical description of product

The subject of this assessment are the post-installed connections, by anchoring or overlap connection joint consisting of steel reinforcing bars (rebars) in existing structures made of normal weight concrete, using injection mortar Torggler Xtreme Epoxy 100 in accordance with the regulations for reinforced concrete construction.

Reinforcing bars with diameters from 8 to 40 mm and Torggler Xtreme Epoxy 100 injection mortar according to Annex A3 are used for the post-installed rebar connections covered by this ETA. The steel element is placed into a drilled hole previously injected with a mortar and is anchored by the bond between embedded element, injection mortar and concrete.

The characteristic material values, dimensions and tolerances of the anchors not indicated in Annexes shall correspond to the respective values laid down in the technical documentation¹ of this European Technical Assessment.

The product description is given in Annex A.

2 Specification of the intended use(s) in accordance with the applicable European Assessment Document (hereinafter EAD)

The performances given in Section 3 are only valid if the rebar connection is used in compliance with the specifications and conditions given in Annex B

The provisions made in this European Technical Assessment are based on an assumed intended working life of the anchor of 50 years and 100 years.

The indications given on the working life cannot be interpreted as a guarantee given by the producer or Assessment Body, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

¹ The technical documentation of this European Technical Assessment is deposited at ETA-Danmark and, as far as relevant for the tasks of the Notified bodies involved in the attestation of conformity procedure, is handed over to the notified bodies.

3 Performance of the product and references to the methods used for its assessment

3.1 Characteristics of product

Mechanical resistance and stability (BWR1):

The essential characteristics are detailed in the Annex C.

Safety in case of fire (BWR2):

Reaction to fire: Rebar connections satisfy requirements for Class A1.

Resistance to fire: See Annex C

3.2 Methods of assessment

The assessment of fitness of the anchor for the intended use in relation to the requirements for mechanical resistance and stability and safety in case of fire in the sense of the Basic Requirements 1 and 2 has been made in accordance with the EAD 330087-01-0601, Systems for post-installed rebar connections with mortar.

4 Assessment and verification of constancy of performance (hereinafter AVCP) system applied, with reference to its legal base


4.1 AVCP system

According to the decision 96/582/EC of the European Commission, the system(s) of assessment and verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) is 1.

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at ETA-Danmark prior to CE marking

Issued in Copenhagen on 2025-10-03 by



Thomas Bruun
Manager, ETA-Danmark

Examples of post-installed rebar connections




Figure 1.2 Overlap joint for rebar connections of slabs and beams




Figure 1.3 Overlap joint at a foundation of a column or wall where the rebar is stressed in tension




Figure 1.4 End anchoring of slabs or beams, designed as simply supported





Figure 1.5 rebar connection for components stressed primarily in compression; rebar is stressed in compression



(only post-installed rebar is plotted)

Key to Figure 1.6

- T acting tensile force
- E envelope of $M_{ed}/z + N_{ed}$ (see EN 1992-1-1 [1], Figure 9.2)
- x distance between the theoretical point of support and concrete joint

Note to Figure 1.2 to 1.6:

In the Figures no transverse reinforcement is plotted, the transverse reinforcement as required by EN 1992-1-1 [1] shall be present.


The shear transfer between old and new concrete shall be designed according to EN 1992-1-1 [1].

Figure 1.6 Anchoring of reinforcement to cover the line of acting tensile force

TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Product description
Use of the product

Annex A1
of European
Technical Assessment
ETA-25/0942



- ① Torggler Xtreme Epoxy 100
- ② Sealing cap
- ③ Mixer
- ④ Rebar - Reinforced bar

TORGLER XTREME EPOXY 100 for post-installed rebar connections

Product description
 Injection system

Annex A2
 of European
 Technical Assessment
 ETA-25/0942

Table A1: Reinforcing bars (Rebar)

Designation	Material
Rebar according to EN 1992-1-1:2011, Annex C	Bars and de-coiled rods Class B or C With f_{yk} and k according to NDP or NCL or EN 1992-1-1:2011/NA $f_{uk} = f_{tk} = k \times f_{yk}$

Rib height h: The rib height h should be: $0,05 \cdot \varnothing \leq h_{rib} \leq 0,07 \cdot \varnothing$

\varnothing = nominal bar diameter

Table A2: Injection mortar


Designation	Material
Torggler Xtreme Epoxy 100 two components injection mortar	Additive: quartz Bonding agent: epoxy resin

TORGLER XTREME EPOXY 100 for post-installed rebar connections


Product description
Materials

Annex A3
of European
Technical Assessment
ETA-25/0942

Xtreme Epoxy 100 - from 385 to 1400 ml cartridge - side by side cartridge



Xtreme Epoxy 100 - 600 ml - foil system



MIXER - the mixer is suitable for each type of cartridge



TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Product description
 Cartridge types and sizes

Annex A4
 of European
 Technical Assessment
 ETA-25/0942

Specification of intended use

Anchorage subject to:

- Static and quasi-static load: from Ø8 to Ø40 mm. For a working life of 50 and 100 years.
- Seismic load: from Ø12 to Ø32 mm. For a working life of 50 and 100 years.
- Fire exposure: from Ø8 to Ø40 mm. For a working life of 50 and 100 years.

Base materials:

- Reinforced or unreinforced normal weight concrete of strength class C12/15 at minimum to C50/60 at maximum according to EN 206-1:2013+A1:2016 for static and quasi-static load and for fire exposure;
- Reinforced or unreinforced normal weight concrete of strength class C16/20 at minimum to C50/60 at maximum according to EN 206-1:2013+A1:2016 for seismic load.
- Maximum chloride content of 0,40% (Cl 0,40) related to the cement content according to EN 206-1:2013+A1:2016.
- Non-carbonated concrete.
- Note: In case of a carbonated surface of the existing concrete structure the carbonate layer shall be removed in the area of the post-installed rebar connections with a diameter of $d_s + 60$ mm prior to the installation of the new rebar. The depth of concrete to be removed shall correspond to at least the minimum concrete cover according to EN 1992-1-1.
- The above may be neglected if building components are new and not carbonated and if building components are in dry conditions.

Temperature range:

- The anchors may be used in the following temperature range:
-40°C to +80°C (max. short term temperature +80°C and max. long term temperature +50°C).
Temperature of the base material according to Annex B4.

Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking into account of the forces to be transmitted.
- Design according to EN 1992-1-1:2011 and EN 1998-1:2004+AC:2009 (see also Annex B2).
- The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing.

Installation:

- Dry or wet concrete (use category I1).
- It must not be installed in flooded holes.
- Installation direction D3 (downward and horizontal and upwards installation).
- Hole drilling by hammer drill (HD), hollow drill bit (HDB), compressed air drill (CA) and diamond drilling machine with dry and wet cutting system (DD).
- Installation of the post-installed rebars shall be done only by suitable trained installer and under supervision on the site.
- Check the position of the existing rebars (if the position of existing rebars in not known it shall be determined using a rebar detector suitable for this purpose as well as on the basis of the construction documentation and then marked on the building component for the overlap joint).


TORGGLER XTREME EPOXY 100 for post-installed rebar connections	Annex B1
Intended use Specification	of European Technical Approval ETA-25/0942

General design rules of construction for post-installed rebars

Post installed rebar may be designed for tension forces only.

The transfer of shear forces between new concrete and existing structure shall be designed additionally according to EN 1992-1-1:2011.

The joints for concreting must be roughened to at least such an extent that aggregate protrude.



* If the clear distance between overlapping rebars is greater than 4·Ø the overlap length shall be enlarged by the difference between the clear distance and 4·Ø.

l₀ – lap length according to EN 1992-1-1:2011. for static and quasi-static loading or EN 1998-1:2004+AC:2009 for seismic loading.

l_v – effective embedment depth; l_v ≥ l₀ + c₁

c – concrete cover of post-installed rebar

c_{min} – minimum concrete cover acc. to Annex B3 and EN 1992-1-1, clause 4.4.1.2.

c₁ – concrete cover at end-face of existing rebar

d₀ – nominal drill bit diameter acc. to Annex B3

Ø – rebar diameter (d_s)

TORGLER XTREME EPOXY 100 for post-installed rebar connections

Intended use
General construction rules for post-installed rebars

Annex B2
of European
Technical Assessment
ETA-25/0942

Table B1: Installation data

Rebar diameter [mm]	Ø8		Ø10		Ø12		Ø14	Ø16	Ø20	Ø22	Ø24-26	Ø28	Ø30	Ø32	Ø36	Ø40
Drill bit diameter [mm]	10	12	12	14	14	16	18	20	25	26-28	30-32	40	35-37	40	45	50-52
Brush diameter [mm]	12	14	14	16	16	18	20	22	27	27-32	32-37	42	37-42	42	47	53-55
Maximum embedment depth l_v , max [mm]	250	700	250	900	250	1100	1300	1400	1800	2000	2200	2500	2500	2500	2500	2500

Installation data for seismic load are valid only from Ø12 to Ø32

Table B2: Minimum concrete cover c_{min} without drilling aid


Drilling method	Rebar diameter ϕ	c_{min}
Hammer drilling (HD) Hollow drill bit (HDB) Diamond drilling (DD)	< 25mm	30 mm+0,06 x $l_v \geq 2\phi$
	≥ 25 mm	40 mm+0,06 x $l_v \geq 2\phi$
Compressed air drilling (CA)	< 25mm	50 mm+0,08 x l_v
	≥ 25 mm	60 mm+0,08 x $l_v \geq 2\phi$

Table B3: Minimum concrete cover c_{min} when using a drilling aid

Drilling method	Rebar diameter ϕ	c_{min}
Hammer drilling (HD) Hollow drill bit (HDB) Diamond drilling (DD)	< 25mm	30 mm+0,02 x $l_v \geq 2\phi$
	≥ 25 mm	40 mm+0,02 x $l_v \geq 2\phi$
Compressed air drilling (CA)	< 25mm	50 mm+0,02 x l_v
	≥ 25 mm	60 mm+0,02 x $l_v \geq 2\phi$

The minimum concrete cover according to EN 1992-1-1:2011 shall be observed.

For minimum concrete cover in case of seismic action $c_{min,seis}$ see Annex C2



Example of drilling aid

Minimum clear spacing between two post-installed rebars:

$$a = 40 \text{ mm} \geq 4 \cdot \phi$$

TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Intended use
Installation data

Annex B3
of European
Technical Assessment
ETA-25/0942

Table B4: Minimum curing time¹⁾

Concrete temperature	Working time	Minimum curing time ³⁾
0°C ²⁾	2 h	96 h
5°C ²⁾	1 h 15 min	48 h
10°C	1 h	24 h
15°C	45 min	18 h
20°C	30 min	12 h
25°C	20 min	10 h
30°C	15 min	5 h
35°C	12 min	5 h
40°C	8 min	5 h


- 1) The minimum time from the end of the mixing to the time when the anchor is loaded
- 2) Minimum resin temperature recommended, for injection between 5°C and 0°C, equal to 10°C.
- 3) In presence of water the curing time must be doubled
- 4) Max resin temperature of 24°C for installation at maximum setting depth

TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Intended use
Curing time

Annex B4
of European
Technical Assessment
ETA-25/0942

Manual Blower pump: nominal dimensions



It is possible to use the mixer extension (see Annex 6) with the manual blower pump.

However it is possible to blow the hole using the mechanical air system (compressed air) also with the mixer extension




Suitable min pressure 6 bar at 6 m³/h
Oil-free compressed air
Recommended air gun with an orifice opening of minimum 3.5 mm in diameter

1) Position to insert the mixer extension

Mixer extension (from 380 mm to 1000 mm) with nominal diameter equal to 10 mm

For the hole with depth greater than 380 mm up to 2500 mm it is possible use the special mixer extension (see Annex B8) for blower operation.



- ① Steel bristles
- ② Steel stem
- ③ Wood handle


Table B5: Standard brush details (manual brush)

Rebar diameter [mm]		Ø8		Ø10		Ø12		Ø14	Ø16
d₀	Nominal drill hole [mm]	10	12	12	14	14	16	18	20
d_b	Brush diameter [mm]	12	14	14	16	16	18	20	22

TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Intended use
Cleaning tools (1)

Annex B5
of European
Technical Assessment
ETA-25/0942



- ① Steel bristles
- ② Steel stem
- ③ Threaded connection for drilling tool extension
- ④ Extension special brush
- ⑤ Drilling tool connection (SDS connection)




Table B6: Special brush details (mechanical brush)

Rebar diameter [mm]		Ø8		Ø10		Ø12		Ø14	Ø16
d₀	Nominal drill hole [mm]	10	12	12	14	14	16	18	20
d_b	Brush diameter [mm]	12	14	14	16	16	18	20	22

Rebar diameter [mm]		Ø20	Ø22	Ø24-26	Ø28	Ø30	Ø32	Ø36	Ø40
d₀	Nominal drill hole [mm]	25	26-28	30-32	35	35-37	40	42-45	50-52
d_b	Brush diameter [mm]	27	27-32	32-37	37	37-42	42	45-47	55

TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Intended use
Cleaning tools (2)


Annex B6
of European
Technical Assessment
ETA-25/0942

Installation with hollow drill bit (HDB)

This drilling method is a hammer drilling method.

This drilling system removes the dust and cleans the bore hole during the drilling operation when used in accordance with the user's manual.

This drilling system include a vacuum cleaner. A suitable dust extraction system must be used. e.g. Bosch GAS 35 M AFC or a comparable dust extraction system with equivalent performance data.



Switch-on the vacuum cleaner before to drill!!!

Table B7: HDB installation diameters


Rebar diameter [mm]		Ø8	Ø10	Ø12	Ø14	Ø16	Ø20	Ø22	Ø24-26	Ø28	Ø30
d₀	Nominal drill hole [mm]	10-12	12-14	14-16	18	20	25	26-28	30-32	35	35

TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Intended use
Hollow drill bit (HDB) specification



Annex B7
of European
Technical Assessment
ETA-25/0942

Use the mixer extension (assembled on the standard mixer) for the injection up to 300 mm if necessary.




Use this system for special conditions:

Tools for installation in special condition



Insert the special mixer extension in the inner diameter of the injection plug up to reach the top of the plug




- ① Injection plug (nominal diameter according to the nominal diameter of drilled hole)
- ② Special mixer extension (variable length with nominal diameter 10 mm)
Mark the required mortar level ℓ_m and embedment depth ℓ_v with tape or marker on the injection extension. Quick estimation: $\ell_m = 1/3 \cdot \ell_v$
Continue injection until the mortar level mark ℓ_m becomes visible.
- ③ Standard mixer (suitable for all size of cartridge)

These tools allow the application in special conditions:
- installation with anchorage depth greater than 300 mm
- overhead installation.

For these applications is recommended the use of the injection pneumatic pump.

System assembled

- ① Injection plug
- ② Special mixer extension
- ③ Standard mixer
- ④ Cartridge
- ⑤ Sample of injection pneumatic pump



TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Intended use
Tools for injection (1)






Annex B8
of European
Technical Assessment
ETA-25/0942



Table B8: Mortar injection dispensers




Injection dispensers	Cartridges	Clean hole tools	Maximum depth of the drill hole
 <p><i>Manual</i></p>	385 ml 585 ml	Blower pump or compressed air and standard brush or special brush or HDB	300 mm*
 <p><i>Manual+ Cartridge Adaptor</i></p>	600 ml Foil system	Blower pump or compressed air and standard brush or special brush or HDB	300 mm*
 <p><i>Battery</i></p>	385 ml 585 ml	Compressed air and special brush or HDB	300 mm to 1000 mm*
 <p><i>Pneumatic</i></p>	385 ml 585 ml 1000 ml 1400 ml	Compressed air and special brush or HDB	300 mm to 2500 mm*

* Note: use the mixer extension described in Annex B8 for the injection of the mortar

<p>TORGGLER XTREME EPOXY 100 for post-installed rebar connections</p>	<p>Annex B9 of European Technical Assessment ETA-25/0942</p>
<p>Intended use Tools for injection (2)</p>	




1		<p>Drill the hole with the correct diameter and depth using a rotary percussive machine. Check the perpendicularity of the hole during the drilling operation. In case of use of hollow drill bit (Annex B7) proceed directly to the point 3</p>
2	 <p>4x Blower Manual Pump 4x Standard Brush 4x Blower Manual Pump</p> <p>if necessary, use a mixer extension for the blower operation (see Annex B5)</p>	<p>Clean the hole from drilling dust: The hole shall be cleaned by at least 4 blowing operations, by at least 4 brushing operations followed again by at least 4 blowing operations; before brushing clean the brush and check (see Annex B5, standard brush) if the brush diameter is sufficient. For the blower tools see Annex B5.</p>
3		<p>Unscrew the front cup, screw on the mixer and insert the cartridge in the gun.</p>
4		<p>Before starting to use the cartridge, eject a first part of the product, being sure that the two components are completely mixed. The complete mixing is reached only after that the product, obtained by mixing the two components, comes out from the mixer with a uniform color.</p>
5	 <p>if necessary, use a mixer extension for the injection (see Annex B8)</p>	<p>Fill the drilled hole uniformly starting from the drilled hole bottom, in order to avoid entrapment of the air; remove the mixer slowly bit by bit during pressing-out; filling the drill hole with a quantity of the injection mortar corresponding to 2/3 of the drill hole depth.</p>
6	 <p>ATTENTION: Use the rods dry and free oil and other contaminants</p>	<p>Insert immediately the rod, marked according to the proper anchorage depth, slowly and with a slight twisting motion, removing excess of injection mortar around the rod. Observe the processing time according Annex B4. Wait the curing time according Annex B4.</p>
<p>TORGLER XTREME EPOXY 100 for post-installed rebar connections</p>		<p>Annex B10</p>
<p>Intended use Installation instruction up to 300 mm depth (HD – HDB – CA)</p>		<p>of European Technical Assessment ETA-25/0942</p>

1	See point 1 Annex B10. In case of use of hollow drill bit (HDB) proceed directly to the point 3.	
2	 <p>4 x 5 seconds 4x 4 x 5 seconds ATTENTION: compressed air free oil</p>	<p>Clean the hole from drilling dust: the hole shall be cleaned by at least 4 blowing operations (5 seconds for single operation) with compressed air, by at least 4 brushing operations with special brush followed again by at least 4 blowing operations (5 seconds for single operation) with compressed air. Before brushing clean the brush and check (see Annex B6, special brush) if the brush diameter is sufficient. For the blower tools see Annex B5.</p>
3	See point 3 Annex B10	
4	See point 4 Annex B10	
5		<p>Before starting the injection, assemble the system according to Annex B8. After that, fill the drilled hole uniformly from the drilled hole bottom, in order to avoid entrapment of the air; remove the special mixer extension with injection plug slowly bit by bit during pressing-out; filling the drill hole with a quantity of the injection mortar corresponding to 2/3 of the drill hole depth. Procedure for overhead application is detailed in Annex B13.</p>
6	See point 6 Annex B10	
TORGLER XTREME EPOXY 100 for post-installed rebar connections		<p>Annex B11 of European Technical Assessment ETA-25/0942</p>
<p>Intended use Procedure up to max anchorage depth (HD – HDB – CA)</p>		

<p>1</p>		<p>Drill the hole with the correct diameter and depth using a core drill machine. Check the perpendicularity of the hole during the drilling operation. Remove completely the core from the hole.</p>
<p>2</p>	 <p>flush hole until water runs clear 4x blower with compressed air 4x special brush 4x blower with compressed air</p>	<p>After operation 1, if the diamond drilling machine used has a dry cutting system to proceed with the installation procedure according to the point 3.</p> <p>Instead, if it is used a wet cutting system before of the point 4 the following operation must be done:</p> <ul style="list-style-type: none"> - flush hole 2 times by inserting a water hose to the back of the hole until water runs clear; - brush 2 times with the proper special brush. Before brushing clean the brush and check (see Annex B6, special brush) if the brush diameter is sufficient; - flush again 2 times until water runs clear; - remove all standing water completely (using for example vacuum system or compressed air free oil).
<p>3</p>	 <p>4 x 5 seconds 6x 4 x 5 seconds</p> <p>ATTENTION: compressed air free oil</p>	<p>Clean the hole from drilling dust: the hole shall be cleaned by at least 4 blowing operations (5 seconds for single operation) with compressed air, by at least 4 brushing operations with special brush followed again by at least 4 blowing operations (5 seconds for single operation) with compressed air. Before brushing clean the brush and check (see Annex B6, special brush) if the brush diameter is sufficient. For the blower tools see the Annex B5.</p>
<p>4</p>	<p>After the operation above, proceed according to the operations from 4 to 6 on the previous Annex B9 and B10 in function of the depth of the hole.</p>	
<p>TORGGLER XTREME EPOXY 100 for post-installed rebar connections</p>		<p>Annex B12 of European Technical Assessment ETA-25/0942</p>
<p>Intended use Procedure with diamond drilling (DD) for all depths</p>		

Overhead installation procedure

In addition to standard procedure, for overhead installation, following the below procedure

<p>1</p> 	<p>1 - Start injection</p> <p>Inject from the bottom of the hole. Maintain this position during the injection phase.</p>
<p>2</p> 	<p>2 - Injection phase</p> <p>Inject the product about 2/3 of the hole depth. During the injection maintain this position to assure the correct installation</p>
<p>3</p> 	<p>3 - End injection</p> <p>Remove the injection plug. Insert immediately the rod (turn the rod during the insertion).</p>
<p>4</p> 	<p>4 - End installation</p> <p>To avoid the slipping of the rod during the open time of the product (due to the rod own weight) use a temporary interlocking element (for ex. wedge of wood)</p>

TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Intended use
Overhead application

Annex B13
of European
Technical Assessment
ETA-25/0942

Minimum anchorage length and minimum lap length under static loading

The minimum anchorage length $l_{b,min}$ and the minimum lap length $l_{0,min}$ according to EN 1992-1-1:2011 shall be multiplied by the relevant amplification factor $\alpha_{lb} - \alpha_{lb,100y}$ given in table C1.

The design bond strength $f_{bd,PIR} - f_{bd,PIR,100y}$ is given in table C3. It is obtained by multiplying the bond strength f_{bd} according to EN 1992-1-1:2011 with the factor $k_b - k_{b,100y}$ according to table C2.

Table C1: Amplification factor $\alpha_{lb} = \alpha_{lb,100y}$ related to the concrete class and drilling method for 50 and 100 years

Concrete Class	Drilling method	Bar size	Amplification factor $\alpha_{lb} = \alpha_{lb,100y}$
C 12/15 to C50/60	All drilling method	8mm to 40 mm	1,0

Table C2: Bond efficiency factor $k_b = k_{b,100y}$ related to concrete class and drilling method for 50 and 100 years

Drilling method and bar size	Concrete class								
	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
for perforation with hammer drill (HD), hollow drill bit (HDB) and compressed air drill (CA)									
da Ø8 a Ø30	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00
Ø32	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00	0,93
Ø36	1,00	1,00	1,00	1,00	1,00	1,00	1,00	0,92	0,86
Ø40	1,00	1,00	1,00	1,00	1,00	1,00	0,91	0,84	0,79
for perforation with diamond drilling machine (DD), dry and wet cutting system.									
da Ø8 a Ø25	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00
Ø28	1,00	1,00	1,00	1,00	1,00	1,00	1,00	0,92	0,86
Ø30	1,00	1,00	1,00	1,00	1,00	1,00	0,91	0,84	0,79
Ø32	1,00	1,00	1,00	1,00	1,00	0,90	0,82	0,76	0,71
Ø36	1,00	1,00	1,00	1,00	1,00	0,90	0,82	0,76	0,71
Ø40	1,00	1,00	1,00	1,00	1,00	0,90	0,82	0,84	0,79

Table C3: Design values of the ultimate bond resistance $f_{bd,PIR} = f_{bd,PIR,100y}$ for 50 and 100 years¹⁾

Drilling method and bar size	Concrete class								
	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
Design bond strength [N/mm²] for perforation with hammer drill (HD), hollow drill bit (HDB) and compressed air drill (CA)									
da Ø8 a Ø30	1,60	2,00	2,30	2,70	3,00	3,40	3,70	4,00	4,30
Ø32	1,60	2,00	2,30	2,70	3,00	3,40	3,70	4,00	4,00
Ø36	1,50	1,90	2,20	2,60	2,90	3,30	3,60	3,60	3,60
Ø40	1,50	1,80	2,10	2,50	2,80	3,10	3,10	3,10	3,10
Design bond strength [N/mm²] for perforation with diamond drilling machine (DD), dry and wet cutting system.									
da Ø8 a Ø25	1,60	2,00	2,30	2,70	3,00	3,40	3,70	4,00	4,30
Ø28	1,60	2,00	2,30	2,70	3,00	3,40	3,70	3,70	3,70
Ø30	1,60	2,00	2,30	2,70	3,00	3,40	3,40	3,40	3,40
Ø32	1,60	2,00	2,30	2,70	3,00	3,00	3,00	3,00	3,00
Ø36	1,50	1,90	2,20	2,60	2,90	2,90	2,90	2,90	2,90
Ø40	1,50	1,80	2,10	2,50	2,80	2,80	2,80	3,10	3,10

¹⁾ Values valid only for good bond condition according to EN 1992-1-1:2011.

For other bond conditions multiply the values for 0,7

Parameter η_2 already included for diameter > 32 mm

TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Performances

Design values of the ultimate bond resistance $f_{bd,PIR} - f_{bd,PIR,100y}$

Annex C1
of European
Technical Assessment
ETA-25/0942

Minimum anchor length and minimum lap length under seismic loading

The minimum anchorage length $l_{b,min}$ and the minimum lap length $l_{o,min}$ according to EN 1992-1-1:2011 shall be multiplied by the relevant amplification factor $\alpha_{lb,seis} - \alpha_{lb,seis,100y}$ given in table C4.

The design bond strength $f_{bd,seis} - f_{bd,seis,100y}$ is given in table C7. It is obtained by multiplying the bond strength f_{bd} according to EN 1992-1-1:2011 with the factor $k_{b,seis} - k_{b,seis,100y}$ according to table C6.

The minimum concrete cover according to Annex B3 and $c_{min,seis} = 2 \varnothing$ applies.

Table C4: Amplification factor $\alpha_{lb,seis} = \alpha_{lb,seis,100y}$ related to the concrete class and drilling method for 50 and 100 years

Concrete Class	Drilling method	Bar size	Amplification factor $\alpha_{lb,seis} = \alpha_{lb,seis,100y}$
C 16/20 to C50/60	Hammer drilling (HD) Hollow drill bit (HDB) Compressed air drilling (CA)	12mm to 32mm	1,0

Table C5: $c_{min,seis}$ – minimum edge distance in case of seismic condition

Design condition	Distance of 1 st edge	Distance of 2 nd edge
Edge	$\geq 4\phi$	$\geq 8\phi$
Corner	$\geq 6\phi$	$\geq 6\phi$

\varnothing = nominal bar diameter

Table C6: Bond efficiency factor $k_{b,seis} = k_{b,seis,100y}$ related to concrete class and drilling method for 50 and 100 years

Drilling method and bar size	Concrete class							
	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
for perforation with hammer drill (HD), hollow drill bit (HDB) and compressed air drill (CA)								
$\varnothing 12$ to $\varnothing 30$	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00
$\varnothing 32$	1,00	1,00	1,00	1,00	1,00	1,00	1,00	0,93

Table C7: Design values of the ultimate bond resistance $f_{bd,PIR,seis} = f_{bd,PIR,seis,100y}$ for 50 and 100 years¹⁾

Drilling method and bar size	Concrete class							
	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
Design bond strength [N/mm ²] for perforation with hammer drill (HD), hollow drill bit (HDB) and compressed air drill (CA)								
$\varnothing 12$ to $\varnothing 30$	2,00	2,30	2,70	3,00	3,40	3,70	4,00	4,30
$\varnothing 32$	2,00	2,30	2,70	3,00	3,40	3,70	4,00	4,00

¹⁾ Values valid only for good bond condition according to EN 1992-1-1:2011. For other bond conditions multiply the values for 0,7

TORGGLER XTREME EPOXY 100 for post-installed rebar connections

Performances
Design values of the ultimate bond resistance $f_{bd,PIR,seis} - f_{bd,PIR,seis,100y}$

Annex C2
of European
Technical Assessment
ETA-25/0942

Design value of the ultimate bond stress $f_{bd,fi} = f_{bd,fi,100y}$ under fire exposure for concrete classes C12/15 to C50/60, (all drilling methods) for 50 and 100 years:

The design value of the bond strength $f_{bd,fi}$ under fire exposure has to be calculated by the following equation:

$$f_{bd,fi}(\theta) = k_{fi}(\theta) \cdot f_{bd,PIR} \cdot \frac{\gamma_c}{\gamma_{M,fi}}$$

If $21^\circ\text{C} \leq \theta \leq 227^\circ\text{C}$: $k_{fi}(\theta) = \frac{1887,34 \cdot \theta^{-1,392}}{f_{bd,PIR} \cdot 4,3} \leq 1,0$

If $\theta > 227^\circ\text{C}$: $k_{fi}(\theta) = 0$

$f_{bd,fi}(\theta)$ = Design value of the ultimate bond stress in case of fire in N/mm²

(θ) = Temperature in °C in the mortar layer

$k_{fi}(\theta)$ = Reduction factor under fire exposure


$f_{bd,PIR}$ = Design value of the ultimate bond stress in N/mm² in cold condition according to Table C3 considering the concrete classes, the rebar diameter, the drilling method and the bond conditions according to EN 1992-1-1

γ_c = Partial safety factor according to EN 1992-1-1:2011

$\gamma_{M,fi}$ = Partial safety factor according to EN 1992-1-2:2011

For evidence under fire exposure the anchorage length shall be calculated according to EN 1992-1-1:2011, equation 8.3 using the temperature-dependent ultimate bond stress $f_{bd,fi}$.

Figure C1: Example graph of Reduction factor $k_{fi}(\theta) = k_{fi,100y}(\theta)$ for concrete classes C20/25 for good bond conditions for 50 and 100 years:



TORGLER XTREME EPOXY 100 for post-installed rebar connections	Annex C3 of European Technical Assessment ETA-25/0942
Performances Design values of bond strength $f_{bd,fi} - f_{bd,fi,100y}$ under fire exposure with temperature reduction factor $k_{fi}(\theta) - k_{fi,100y}(\theta)$	